



# Venture Tape

30 Commerce Road  
Rockland, MA 02370-0384

17/10/2007

781-871-1400  
Fax: 781-871-0065

## 1585CEL

### CELOTEX SHEATHING TAPE

**DESCRIPTION:** A thin, strong, polypropylene film coated with an aggressive cold weather acrylic adhesive system. This system was specially formulated to have excellent performance characteristics at both sub-freezing temperatures and elevated temperatures along with good quick stick for ease in applying.

**APPLICATIONS:** Used primarily as a closure system and vapor seal on Celotex SUPER TUFF-R and TUFF WEATHER WRAP. Also recommended for use on all exterior sheathing materials such as Tyvek sheeting, plywood, OSB, Dens Glass Gold®, thermal insulation and all exterior vapor barriers including and Typar® housewraps. Can also be used to repair rips, punctures and tears on interior vapor barrier systems. This tape can be applied to door and window flanges, sill plates, corners, and joints to improve air tightness.

### TECHNICAL DATA

	<u>IMPERIAL</u>	<u>METRIC</u>
<b>Thickness:</b>	3 mils (.003")	0.076 mm
<b>Adhesion: Peel:</b>	(oz/inch)	(N/100mm)
<b>Tyvek®</b>	28.0 oz/inch	7.95 N/2.5 cm
<b>Polyethylene</b>	16.0 oz/inch	4.5 N/2.5 cm
<b>Stainless Steel</b>	65.0 oz/inch	18.4 N/2.5 cm
<b>Shear: 96 hrs @</b>	2.2 psi	15.2 kPa
<b>Hot Shear: 20 minutes @</b>	150°F/2.2 psi	66°C/15.2kPa
<b>Tensile:</b>	20 lbs./inch width	91 N/2.5 cm
<b>Elongation:</b>	136%	136%
<b>WVTR:</b>	0.16 grams/per 100sq inch	
<b>Shelf Life:</b>	Recommend one year from date of receipt by customer when stored under optimum conditions (70°F, 50% RH).	
	*Dens Glass Gold® is a registered trademark of Georgia Pacific Gypsum Corp.	
	*Tyvek® is a registered trademark of E.I. Dupont de Nemours & Co. Inc.	
	*Typar® is a registered trademark of Reemay, Inc.	

#### **IMPORTANT INFORMATION:**

The information cited is in good faith and has been established from sources held to be secure and reliable. The values listed are typical properties and are not intended to be used as specifications for defined applications. User must determine the product suitability for the end use application and assume all risks and liabilities. 1/28/00