


Knauf Phenolic Laminate



CFC and HCFC free phenolic foam bonded to 9.5mm Knauf Wallboard. Phenolic Laminate has a vapour check incorporated within its construction.

Knauf Phenolic Laminate has a Thermal Conductivity figure for Vapourshield of 0.18W/mK and for Phenolic Foam of 0.022W/mK (60mm and 65mm boards) or 0.018W/mK (50mm boards).

Thermal Resistance:
 50mm = 1.82m² K/W
 60mm = 2.36m² K/W
 65mm = 2.58m² K/W

Dimensions (mm)			Article No	Pack Details		
Thickness	Width	Length		Boards	m ²	Tonnes (Approx.)
50.0	1200	2400	475 60 724	20	57.6	0.46
60.0	1200	2400	475 60 824	16	46.1	0.37
65.0	1200	2400	475 60 924	15	43.2	0.35